

DCC Orange 7136



The best coatings are made with the best pigments

DCC Orange 7136

Excellent opacity, rheology and weatherfastness/solvent resistance.

Replacement for Molybdate Orange

coatings



Dominion Colour Corporation

Working Together for Quality

ISO 9001
ISO 14001

www.dominioncolour.com
sales@dominioncolour.com

DCC Orange 7136

Pigment Orange 36



CHEMICAL CLASS

Benzimidazolone
C.A.S. # 12236-62-3

PRODUCT OVERVIEW

DCC Orange 7136 is a high performance blue shade orange pigment for use in high-end coatings applications. It can be used in all coatings but is recommended for the highest end coatings applications where excellent weatherfastness, heat stability, chemical resistance, rheology and dispersion are required.

SHADE INDICATOR



THIS PRODUCT RANGE IS SUPPORTED BY:

- DCC's global presence
- DCC's technical service and support
- Local warehousing capabilities that ensure on-time delivery
- DCC's ability to consistently deliver quality products

APPLICATIONS

	DCC Orange 7136
Architectural Water & Universal	■
Architectural Solvent	■
Industrial Fast Air Drying	■
Industrial Oven Cured	■
Coil Coatings	□
Automotive Coatings	■
Powder Coatings	■




RESISTANCE PROPERTIES

	DCC Orange 7136
Ethyl Acetate	E
Ethyl Alcohol	E
MEK	E
Mineral Spirits	E
Water	E
Xylene	E
Dilute Alkali	E
Dilute Acid	E



PRODUCT CHARACTERISTICS

	DCC Orange 7136
Weatherfastness	
• Masstone	5
• Tint	4
Physical Properties	
• Specific Gravity	1.61
• Oil Absorption	37
• Heat Resistance	200°C



LEGEND: E - Excellent VG - Very Good G - Good F - Fair P - Poor **RECOMMENDATIONS:** ■ Frequently Used □ Limited Use □ Not Normally Used
WEATHERFASTNESS: 1 - Severe Change In Shade 5 - No Change In Shade

The information in this handout is based on extensive testing and application experience and is believed to be a reliable indication of the results that may be expected. However, the data does not constitute a specification for the products, and is offered only as a guide to performance without guarantee or warranty of any kind. Because of the difficulties of modern colour reproduction, the shades may vary slightly from the final colour application. Since many variables have a strong influence on pigment performance, the users are encouraged to test each product in their own laboratory prior to use.



Dominion Colour Corporation
Working Together for Quality

ISO 9001
ISO 14001

www.dominioncolour.com
sales@dominioncolour.com

DISTRIBUTED BY: _____